

EPOXY SELFLEVELLING FLOORING

Solvent Free High Build Epoxy Coating

► Description

To provide a tough, hard wearing, easily cleaned surface in industrial environments where a degree of higher resistance to load & chemical attack is required. It is suitable for use in workshops, production and processing areas, dairies, soft drinks and bottling plants, breweries, kitchens any floor areas subject to wet working and possible chemical spillage.

Features

Hard wearing-durable with low maintenance costs
Resistant to a wide range of chemicals and liquids
Easily cleaned
Provides a high gloss finish
Conforms to the overall migration standards laid down in 21 CFR 157-300 of US - FDA certified by CFTRI.

Physical Properties

Selflevelling	@27+1 C
Pot Life	30 minutes
Time between coats	8 - 24 hours
Walkability	24 hours
Full Cure	7 days
Dry film thickness	200 ² microns per coat

► for two or more coats

Coverage Estimates

Pack Size	Coverage
6kg	15 - 20m ² per pack per coat at microns per coat



Note : These figures are theoretical, due to wastage and the variety and nature of substrates practical coverage figures may

► be reduced.

Storage and Shelf Life

Epoxy flooring has a shelf life of 12 months when stored in normal dry conditions.

